

Technological Data

lahnur® 330.200

Impregnated special paper

Variable	Test Method	Unit	Average
Grammage	DIN EN ISO 536	g/m ²	200
Thickness	DIN EN ISO 534	µm	236
Apparent density	DIN EN ISO 534	g/cm ³	0,85
Tensile strength md.	DIN EN ISO 1924-2	N/15mm	196
Tensile strength cd.	DIN EN ISO 1924-2	N/15mm	115
Tensile stretch md.	DIN EN ISO 1924-2	%	6,3
Tensile stretch cd.	DIN EN ISO 1924-2	%	10
Wet tensile strength md.	DIN ISO 3781	N/15mm	17
Water absorption (Cobb) top s.	DIN EN 20 535	g/m ²	30
Tear resistance md.	DIN EN ISO 1974	mN	2500
Tear resistance cd.	DIN EN ISO 1974	mN	2900
Roughness Bendtsen top s.	DIN EN 53 120, T.1	ml/min	350
Roughness Bendtsen back s.	DIN EN 53 120, T.1	ml/min	400
Whiteness	DIN 53 145, T.1	%	85
Opacity	DIN 53 146	%	94

These values are approximate values and do not represent a specification.

The information contained in this document is based on our knowledge and practical experience. Due to the variety of possible influences during processing and use we recommend that the customers carry out own trials to test our products. Changes due to technical progress or internal development are reserved. A legally binding guarantee of certain properties cannot be derived from the statements in this document.