



## Technické dáta: IQ selection smooth

			160	200	250	300
Plošná hmotnosť	g/m <sup>2</sup>	ISO 536	160 ± 6.0	200 ± 6.0	250 ± 7.0	300 ± 8.0
Hrúbka	µm	ISO 534	176 ± 6	214 ± 7	262 ± 8	315 ± 10
Tuhost' L&W	MDmN	ISO 2493-1	550 ± 50	min 800	min 1200	min 2000
Tuhost' L&W	CD mN	ISO 2493-1	300 ± 40	min 400	min 650	min 1000
Hladkosť Bekk	sec	ISO 5627	70 ± 15	60 ± 15	60 ± 15	50 ± 15
Opacita	%	ISO 2471	97.0 ± 1	99.0 ± 1	99.0 ± 1	99.0 ± 1
Belosť s UV	D65%	ISO 2470	113.5 ± 1.5	113.5 ± 1.5	113.5 ± 1.5	113.5 ± 1.5
CIE Belosť		ISO 11475	170 ± 3.0	170 ± 3.0	170 ± 3.0	170 ± 3.0

Výrobok spĺňa EN 12281, požiadavky na kopírovací papier pre rozmnožovanie suchým tonerom a ISO 9706, požiadavky pre stálosť papiera. Výrobné procesy certifikované podľa ISO 9001, ISO 14001 a OHSAS 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA



0  
8  
5  
1  
5  
0  
A

