

Technological DataPage: 1
2014-01-20
en**pretex® 30.120**

Impregnated special paper

| Variable | Test method | Unit | Value |
|--------------------------|-------------------|-------------------|-------|
| Grammage | DIN EN ISO 536 | g/m ² | 120 |
| Thickness | DIN EN ISO 534 | µm | 142 |
| Apparent density | DIN EN ISO 534 | g/cm ³ | 0,85 |
| Tensile strength md. | DIN EN ISO 1924-2 | N/15mm | 144 |
| Tensile strength cd. | DIN EN ISO 1924-2 | N/15mm | 102 |
| Tensile stretch md. | DIN EN ISO 1924-2 | % | 3,1 |
| Tensile stretch cd. | DIN EN ISO 1924-2 | % | 7,2 |
| Wet tensile strength md. | DIN ISO 3781 | N/15mm | 49 |
| Wet tensile strength cd. | DIN ISO 3781 | N/15mm | 35 |
| Tear resistance md. | DIN EN 21 974 | mN | 1200 |
| Tear resistance cd. | DIN EN 21 974 | mN | 1350 |
| Whiteness | DIN 53 145, T.1 | % | 88 |
| Opacity | DIN 53 146 | % | 90 |

These values are approximate values and do not represent a specification.

The information contained in this document is based on our knowledge and practical experience. Due to the variety of possible influences during processing and use we recommend that the customers carry out own trials to test our products. Changes due to technical progress or internal development are reserved. A legally binding guarantee of certain properties cannot be derived from the statements in this document.