



**Technical Data/  
Technická data:**

**Color Copy coated glossy**

<b>Grammage/ Gramáž</b>	g/m <sup>2</sup>	ISO 536		<b>170</b>	<b>± 4.0</b>
<b>Caliper/ Tloušťka</b>	mm/1000	ISO 534		<b>136</b>	<b>± 6</b>
<b>Smoothness Bekk/ Hladkost dle Bekka</b>	sec	ISO 5627		<b>500</b>	<b>± 150</b>
<b>Opacity/ Opacita</b>	%	ISO 2471	<b>min</b>	<b>96.0</b>	
<b>Moisture Abs/ Absolutní vlhkost</b>	%	ISO 287		<b>4.8</b>	<b>±.6</b>
<b>Brightness with UV/ Bělost s UV</b>	%	ISO 2470		<b>103.0</b>	<b>± 2.0</b>
<b>CIE Whiteness/ CIE bělost</b>	%	ISO 11475		<b>139</b>	<b>± 2.5</b>
<b>Gloss 75°/ Lesk 75°</b>		TAPPI T 480		<b>78</b>	<b>± 4</b>

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001.

Produkt splňuje EN 12281, požadavky pro kopírovací papír pro tisk na bázi suchého toneru a ISO 9706, požadavky na stálost papíru. Výrobní proces je certifikován ISO 9001.

SIGNIFICANCE OF VALUES: 2 SIGMA  
HRANICE HODNOT: 2 SIGMA

TECHNICAL CUSTOMER SERVICE



