



IQ PRINT will win over every printer. This uncoated, wood-free paper combines excellent runnability and superior surface properties.



### Technical Data: IQ PRINT

			300	350	400
<b>Basis weight</b>	g/m <sup>2</sup>	ISO 536	<b>300</b> ± 10.0	<b>350</b> ± 10.0	<b>400</b> ± 15.0
<b>Caliper</b>	µm	ISO 534	<b>346</b> ± 10	<b>400</b> ± 12	<b>445</b> ± 15
<b>Roughness Bendtsen</b>	ml/min	ISO 8791-2	<b>225</b> ± 75	<b>225</b> ± 75	<b>225</b> ± 75
<b>Moisture abs.</b>	%	ISO 287	<b>6.2</b> ± .7	<b>6.2</b> ± .7	<b>6.2</b> ± .7
<b>Brightness UV</b>	%	ISO 2470	<b>103.5</b> ± 1.5	<b>103.5</b> ± 1.5	<b>103.5</b> ± 1.5
<b>CIE Whiteness</b>	%	ISO 11475	<b>145</b> ± 3.0	<b>145</b> ± 3.0	<b>145</b> ± 3.0

Product meets DIN 19306-2, Printing paper - part 2: Technical delivery specifications for offset paper, coated and uncoated, white and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

